



上海楚源国际贸易有限公司

Shanghai Chuyuan international trading co.,ltd

LAB TEST REPORT

CY20191125ZY-01 GL PPGL order

PPGL 0.45x1092mm (26GA x 43") 34coils 96.894mt

Requirement: AZ60

Paint: Top 5+20mic/ Back 7mic SMP organic coating from AkzoNobel or Beckers

Yield strength: 90-100KSI


Tensile strength: 95-105KSI

Elongation: 3-7%

100% tension levelled.

Rockwell hardness: 85-90


Beckers SMP paint





上海楚源国际贸易有限公司
Shanghai Chuyuan international trading co.,ltd

Finished coil:



After packing:






上海楚源国际贸易有限公司
Shanghai Chuyuan international trading co.,ltd

1. Color Match

colour aberration less than 0.2



2. T-bend test





3. MEK rub test

200times PASS





4. Paint thickness test

Test Result: total top coating is 42mic
estimates AZ60 coating as 7-8mic
top paint thickness is 34mic
(order requirement 5+20mic).

